



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Acetaldehyde	2	3	1	1	4	3	3	4	2	4	3
Acetamide	4	4	1	1	1	2	2	4	2	2	1
Acetic Acid, Glacial	2	2	2	1	3	4	3	4	2	3	3
Acetic Acid, 30%	2	2	2	1	2	1	2	4	1	2	1
Acetic Anhydride	2	2	2	2	3	2	1	4	3	4	4
Acetone	3	3	1	1	4	3	2	4	3	4	4
Acetophenone	4	4	1	1	4	4	4	4	4	4	4
Acetyl Chloride	4	4	4	4	4	4	4	4	3	1	1
Acetylene	2	2	1	1	1	2	2	4	2	1	1
Acrylonitrile	4	4	4	4	4	4	3	4	4	3	4
Adipic Acid	1	1	1	1	1	1	-	-	-	1	1
Alkazene (Dibromoethylbenzene)	4	4	4	4	4	4	4	4	4	2	2
Alum-NH3-Cr-K (aq)	1	1	1	1	1	1	1	-	1	4	-
Aluminum Acetate (aq)	1	2	1	1	2	2	1	4	4	4	4
Aluminum Chloride (aq)	1	1	1	1	1	1	1	3	2	1	1
Aluminum Fluoride (aq)	2	1	1	1	1	1	1	3	2	1	1
Aluminum Nitrate (aq)	1	1	1	1	1	1	1	3	2	1	1
Aluminum Phosphate (aq)	1	1	1	1	1	1	1	-	1	1	1
Aluminum Sulfate (aq)	1	1	1	1	1	1	1	4	1	1	1
Ammonia Anhydrous	4	4	1	1	2	1	1	4	3	4	4
Ammonia Gas (cold)	1	1	1	1	1	1	1	3	1	4	4
Ammonia Gas (hot)	4	4	2	2	4	2	2	4	1	4	4
Ammonium Carbonate (aq)	1	1	1	-	4	1	-	4	-	1	1
Ammonium Chloride (aq)	1	1	1	1	1	1	1	1	-	1	1
Ammonium Hydroxide (conc.)	4	4	1	1	4	1	1	4	1	2	1
Ammonium Nitrate (aq)	3	2	1	1	1	1	1	4	-	1	1
Ammonium Nitrite (aq)	1	1	1	1	1	1	1	-	2	1	1
Ammonium Persulfate (aq)	1	4	1	1	4	1	1	4	-	1	1
Ammonium Phosphate (aq)	1	1	1	1	1	1	1	-	1	1	1
Ammonium Sulfate (aq)	1	1	1	1	1	1	1	1	-	2	1
Amyl Acetate (Banana Oil)	4	4	3	3	4	4	4	4	4	4	4
Amyl Alcohol	2	2	1	1	2	2	1	4	4	2	1
Amyl Borate	4	4	4	4	1	1	1	-	-	1	1
Amyl Chloronapthalene	4	4	4	4	4	4	4	4	4	1	1
Amyl Napthalene	4	4	4	4	4	4	4	4	4	-	-
Aniline	4	4	1	1	4	4	3	4	4	3	1
Aniline Dyes	2	2	2	1	4	2	2	4	3	2	1
Aniline Hydrochloride	2	4	2	2	2	4	4	4	4	2	1
Animal Fats	4	4	2	2	1	2	2	1	2	1	1
Ansul Ether (Anesthetics)	4	4	3	3	3	4	4	2	4	4	4
Aqua Regia	4	4	4	3	4	4	2	4	4	2	1
Aroclor, 1248	4	4	3	3	3	4	1	4	2	1	1
Aroclor, 1254	4	4	4	3	4	4	4	4	3	1	1
Aroclor, 1260	1	1	1	1	1	1	1	4	2	1	1
Arsenic Acid	2	1	1	1	1	1	1	3	1	1	1
Arsenic Trichloride (aq)	4	4	3	3	1	1	-	-	-	4	4
Askarel	4	4	4	4	2	4	4	4	4	1	1
Asphalt	4	4	4	4	2	2	2	2	4	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Banana Oil (Amyl Acetate)	4	4	3	3	4	4	4	4	4	4	4
Barium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Barium Hydroxide (aq)	1	1	1	1	1	1	1	4	1	1	1
Barium Sulfate (aq)	1	1	1	1	1	1	1	1	1	1	1
Barium Sulfide (aq)	1	2	1	1	1	1	1	1	1	1	1
Beer	1	1	1	1	1	1	1	2	1	1	1
Beet Sugar Liquors	1	1	1	1	1	2	1	4	1	1	1
Benzaldehyde	4	4	1	1	4	4	1	4	2	4	4
Benzene	4	4	4	4	4	4	4	3	4	1	1
Benzene Sulfonic Acid	4	4	4	3	4	2	1	4	4	1	1
Benzene (Ligroin)	4	4	4	4	1	3	2	2	4	1	1
Benzoic Acid	4	4	4	3	3	4	4	4	3	1	1
Benzoyl Chloride	4	4	4	4	4	4	4	-	-	2	1
Benzyl Alcohol	4	4	1	1	4	2	2	4	2	1	1
Benzyl Benzoate	4	4	2	2	4	4	4	-	-	1	1
Benzyl Chloride	4	4	4	4	4	4	4	4	4	1	1
Biphenyl (Diphenyl) (Phenylbenzene)	4	4	4	4	4	4	4	4	4	1	1
Blast Furnace Gas	4	4	4	4	4	4	4	4	1	1	1
Bleach Solutions	4	4	1	1	4	4	1	4	2	1	1
Borax	2	2	1	1	2	1	1	1	2	1	1
Bordeaux Mixture	2	2	1	1	2	2	1	4	2	1	1
Boric Acid	1	1	1	1	1	1	1	1	1	1	1
Brine	1	1	1	1	1	1	1	2	1	1	1
Bromine-Anhydrous	4	4	4	4	4	4	4	4	4	1	1
Bromine Trifluoride	4	4	4	4	4	4	4	4	4	4	4
Bromine Water	4	4	3	2	1	4	1	4	4	1	1
Bromobenzene	4	4	4	4	4	4	4	4	4	1	1
Bunker Oil	4	4	4	4	1	4	4	2	2	1	1
Butadiene	4	4	4	3	4	4	3	4	4	1	1
Butane	4	4	4	4	1	1	2	1	4	1	1
Butter (Animal Fat)	4	4	2	1	1	2	2	1	2	1	1
Butyl Acetate	4	4	3	3	4	4	4	4	4	4	4
Butyl Acetyl Ricinoleate	4	4	1	1	3	2	2	4	-	1	1
Butyl Acrylate	4	4	4	4	4	4	4	-	-	4	4
Butyl Alcohol	1	1	2	2	1	1	1	4	2	1	1
Butyl Amine	4	4	3	2	3	4	4	4	4	4	4
Butyl Benzoate	3	2	2	2	4	4	4	-	-	1	1
Butyl Carbitol	4	4	1	1	4	3	2	-	4	3	2
Butyl Cellosolve	4	4	1	1	3	3	2	4	-	4	4
Butyl Oleate	4	4	2	2	4	4	4	-	-	1	1
Butyl Stearate	4	4	3	3	2	4	4	-	-	1	1
Butylene	4	4	4	4	2	3	4	4	4	1	1
Butyraldehyde	4	4	2	2	4	3	4	4	4	4	4
Calcium Acetate (aq)	1	4	1	1	2	2	2	4	4	4	4
Calcium Bisulfite (aq)	4	4	4	4	4	1	1	1	1	1	1
Calcium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Calcium Hydroxide (aq)	1	1	1	1	1	1	1	1	1	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Calcium Hypochlorite (aq)	3	3	1	1	2	3	1	4	2	1	1
Calcium Nitrate (aq)	1	1	1	1	1	1	1	1	2	1	1
Calcium Sulfide (aq)	2	2	1	1	1	1	1	1	2	1	1
Cane Sugar Liquors	1	1	1	1	1	1	1	4	1	1	1
Carbamate	4	4	2	2	3	2	2	4	-	1	1
Carbitol	2	2	2	2	2	2	2	4	2	2	2
Carbolic Acid (Phenol)	4	4	1	1	4	3	4	3	4	1	1
Carbon Bisulfide	4	4	4	4	3	4	4	-	4	1	1
Carbon Dioxide	2	2	2	2	1	2	2	1	2	1	1
Carbonic Acid	1	2	2	2	2	1	1	1	1	1	1
Carbon Monoxide	2	2	1	1	1	2	2	1	1	1	1
Carbon Tetrachloride	4	4	4	4	3	4	4	4	4	1	1
Castor Oil	1	1	2	2	1	1	2	1	1	1	1
Cellosolve	4	4	2	2	4	4	4	4	4	2	1
Cellosolve Acetate	4	4	2	2	4	4	4	4	4	1	1
Cellulube (Fryquel)	4	4	1	1	4	4	4	4	1	1	1
China Wood Oil (Tung Oil)	4	4	3	3	1	2	3	3	4	1	1
Chlorine (Dry)	4	4	4	4	4	3	2	4	4	1	1
Chlorine (Wet)	4	4	3	3	4	3	3	4	4	1	1
Chlorine Dioxide	4	4	3	3	4	4	3	4	-	1	1
Chlorine Trifluoride	4	4	4	4	4	4	4	4	4	1	1
Chloroacetic Acid	4	4	2	1	4	4	1	4	-	1	1
Chloroacetone	4	4	2	1	4	3	3	4	4	1	1
Chlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Chlorobromomethane	4	4	2	2	4	4	4	4	4	1	1
Chlorobutadiene	4	4	4	4	4	4	4	4	4	1	1
Chlorododecane	4	4	4	4	4	4	4	4	4	1	1
Chloroform	4	4	4	4	4	4	4	4	4	1	1
O-Chloronaphthalene	4	4	4	4	4	4	4	4	4	1	1
1-Chloro-1-Nitro Ethane	4	4	4	4	4	4	4	4	4	4	4
Chlorosulfonic Acid	4	4	4	4	4	4	4	4	4	4	4
Chlorotoluene	4	4	4	4	4	4	4	4	4	1	1
Chlorox (Sodium Hypochlorite NaOC1)	4	4	2	2	2	1	2	4	2	1	1
Chrome Plating Solutions	4	4	2	2	4	4	4	4	2	1	1
Chromic Acid	4	4	3	3	4	3	2	4	3	1	1
Citric Acid	1	1	1	1	1	1	1	1	1	1	1
Coal Tar (Creosote)	4	4	4	4	1	2	4	3	4	1	1
Cobalt Chloride (aq)	1	1	1	1	1	1	1	4	2	1	1
Cocoonut Oil	4	4	3	3	1	2	3	2	1	1	1
Cod Liver Oil	4	4	1	1	1	2	2	1	2	1	1
Coke Oven Gas	4	4	4	4	4	4	3	4	2	1	1
Copper Acetate (aq)	1	4	1	1	2	2	2	4	4	4	4
Copper Chloride (aq)	1	1	1	1	1	2	2	1	1	1	1
Copper Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Copper Sulfate (aq)	2	2	2	1	1	1	1	1	1	1	1
Corn Oil	4	4	3	3	1	3	2	1	1	1	1
Cottonseed Oil	4	4	3	2	1	2	2	1	1	1	1
Creosote (Coal Tar)	4	4	4	4	1	2	4	3	4	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Cresol	4	4	4	4	4	3	4	4	4	1	1
Cresylic Acid	4	4	4	4	4	3	4	4	4	1	1
Cumene	4	4	4	4	4	4	4	4	4	1	1
Cyclohexane	4	4	4	4	1	3	4	1	4	1	1
Cyclohexanol	4	4	4	3	3	1	2	-	4	1	1
Cyclohexanone	4	4	2	2	4	4	4	4	4	4	4
P-Cymene	4	4	4	4	4	4	4	4	4	1	1
Decalin	4	4	4	4	4	4	4	-	4	1	1
Decane	4	4	4	4	1	2	2	2	2	1	1
Denatured Alcohol	1	1	1	1	1	4	3	4	1	1	1
Detergent Solutions	2	2	1	1	1	4	4	4	1	1	1
Developing Fluids	1	2	2	2	1	1	-	-	1	1	1
Diacetone	4	4	1	1	4	4	4	4	4	4	3
Diacetone Alcohol	4	4	1	1	4	2	2	4	2	4	3
Dibenzyl Ether	4	4	2	2	4	3	4	2	-	4	4
Dibenzyl Sebecate	4	4	2	2	4	4	4	2	3	2	1
Dibromoethylbenzene (Alkazene)	4	4	4	4	4	4	4	4	4	2	1
Dibutyl Amine	4	4	4	3	4	4	4	4	3	4	4
Dibutyl Ether	4	4	3	3	4	3	4	2	4	3	3
Dibutyl Phthalate	4	4	3	2	4	4	4	3	2	3	1
Dibutyl Sebecate	4	4	2	2	4	4	4	4	2	2	1
O-Dichlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Dichloro-Isopropyl Ether	4	4	4	3	4	4	4	2	4	3	3
Dicyclohexylamine	4	4	4	4	3	4	4	4	-	4	4
Diesel Oil	4	4	4	4	1	3	3	3	4	1	1
Diethylamine	2	2	2	2	2	2	3	3	2	4	4
Diethyl Benzene	4	4	4	4	4	4	4	4	4	1	1
Diethyl Ether	4	4	4	4	4	3	3	1	4	4	4
Diethylene Glycol	1	1	1	1	1	1	1	4	2	1	1
Diethyl Sebecate	4	4	2	2	2	4	2	4	2	2	1
Diisobutylene	4	4	4	4	2	4	4	4	4	1	1
Diisopropyl Benzene	4	4	4	4	4	4	4	-	-	1	1
Diisopropyl Ketone	4	4	1	1	4	4	4	4	4	4	4
Diisopropylidene Acetone (Phorone)	4	4	3	3	4	4	4	4	4	4	4
Dimethyl Aniline (Xylidine)	3	3	3	2	3	3	4	4	4	4	4
Dimethyl Ether (Methyl Ether) (Monomethyl Ether)	4	4	4	4	1	3	3	-	1	4	4
Dimethyl Formamide	4	4	2	2	2	3	4	4	2	4	4
Dimethyl Phthalate	4	4	2	2	4	4	4	-	-	2	1
Dinitrotoluene	4	4	4	4	4	4	4	4	4	4	4
Diocyl Phtalate	4	4	2	2	3	4	4	4	3	2	1
Diocyl Sebecate	4	4	2	2	4	4	4	2	3	2	1
Dioxane	4	4	2	2	4	4	4	4	4	4	4
Dioxolane	4	4	3	2	4	4	4	4	4	4	4
Dipentene	4	4	4	4	2	4	4	4	4	1	1
Diphenyl (Biphenyl) (Phenylbenzene)	4	4	4	4	4	4	4	4	4	1	1
Diphenyl Oxides	4	4	4	4	4	4	4	4	3	1	1
Dowtherm Oil	4	4	4	4	4	4	4	3	3	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect 3 = Static Only - = Insufficient Data
2 = Moderate Effect 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Dry Cleaning Fluids	4	4	4	4	3	4	4	4	4	1	1
Epichlorohydrin	4	4	2	2	4	4	4	4	4	4	4
Ethane	4	4	4	4	1	2	2	3	4	1	1
Ethanolamine	2	2	2	2	2	2	3	3	2	4	4
Ethyl Acetate	4	4	2	2	4	3	4	4	2	4	4
Ethyl Acetoacetate	3	3	2	2	4	3	4	4	2	4	4
Ethyl Acrylate	4	4	2	2	4	4	4	4	2	4	4
Ethyl Alcohol	1	1	1	1	1	1	1	4	1	2	1
Ethyl Benzene	4	4	4	4	1	4	4	4	4	1	1
Ethyl Benzoate	1	1	1	1	4	4	4	4	4	1	1
Ethyl Cellosolve	4	4	4	4	4	4	4	4	4	4	4
Ethyl Cellulose	2	2	2	2	2	2	2	2	3	4	4
Ethyl Chloride	4	4	4	3	1	4	4	2	4	1	1
Ethyl Chloroformate	4	4	3	2	4	4	4	4	4	1	1
Ethyl Chloroformate	4	4	3	2	4	4	4	4	4	4	4
Ethyl Ether	4	4	3	3	3	3	4	3	4	4	4
Ethyl Formate	4	4	2	2	4	2	2	-	-	1	1
Ethyl Mercaptan	4	4	4	3	4	3	2	-	3	2	1
Ethyl Oxalate	1	1	1	1	4	3	4	1	4	1	1
Ethyl Pentachlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Ethyl Silicate	2	2	1	1	1	1	2	-	-	1	1
Ethylene	3	3	2	2	1	3	-	-	-	1	1
Ethylene Chloride	4	4	3	3	4	4	4	4	4	2	1
Ethylene Chlorohydrin	2	2	2	2	3	2	2	4	3	1	1
Ethylene Diamine	1	2	1	1	1	1	2	4	1	4	4
Ethylene Dichloride	4	4	3	3	4	4	4	4	4	1	1
Ethylene Glycol	1	1	1	1	1	1	1	4	1	1	1
Ethylene Oxide	4	4	3	3	4	4	4	4	4	4	4
Ethylene Trichloride	4	4	3	3	4	4	4	4	4	1	1
Fatty Acids	4	4	3	3	2	2	2	-	3	1	1
Ferric Chloride (aq)	1	1	1	1	1	1	1	1	2	1	1
Ferric Nitrate (aq)	1	1	1	1	1	1	1	1	3	1	1
Ferric Sulfate (aq)	1	1	1	1	1	1	1	1	2	1	1
Fish Oil	4	4	4	4	1	4	-	-	1	1	1
Fluorinated Cyclic Ethers	4	4	1	1	-	4	-	-	-	-	2
Fluorine (Liquid)	4	4	4	4	4	4	-	4	4	2	1
Fluorobenzene	4	4	4	4	4	4	-	4	4	1	1
Fluoroboric Acid	1	1	1	1	1	1	1	-	-	-	2
Fluorocarbon Oils	2	2	1	1	-	2	-	-	-	-	2
Fluorolube	2	3	1	1	1	2	1	-	1	2	1
Fluosilicic Acid	2	3	2	2	1	2	1	-	4	1	1
(Hydrofluosilicic Acid)											
Formaldehyde (RT)	2	2	1	1	3	2	1	4	2	4	4
Formic Acid	2	1	1	1	2	1	1	3	2	3	4
Freon 11	4	4	4	4	2	3	1	4	4	2	2
Freon 12	2	1	2	2	1	1	1	1	4	2	2
Freon 13	1	1	1	1	1	1	1	-	4	2	2
Freon 21	4	4	4	4	4	4	4	-	4	4	4

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Freon 22	2	1	1	1	4	1	1	4	4	4	4
Freon 31	2	4	1	1	4	2	2	-	-	4	4
Freon 32	1	1	1	1	1	1	1	-	-	4	4
Freon 112	4	3	4	4	2	3	2	-	4	2	2
Freon 113	3	2	4	3	1	1	1	2	4	3	3
Freon 114	1	1	1	1	1	1	1	1	4	2	2
Freon 115	1	1	1	1	1	1	1	-	-	2	2
Freon 142b	2	2	1	2	1	1	1	-	-	4	4
Freon 152a	1	1	1	1	1	1	3	-	-	4	4
Freon 218	1	1	1	1	1	1	1	-	-	2	2
Freon C316	1	1	1	1	1	1	1	-	-	2	2
Freon C318	1	1	1	1	1	1	1	-	-	2	2
Freon 13B1	1	1	1	1	1	1	1	1	4	2	2
Freon 114B2	4	3	4	4	2	3	1	-	4	2	2
Freon 502	1	1	1	1	2	1	-	-	-	4	4
Freon TF	4	3	4	4	1	1	1	1	4	2	2
Freon T-WD602	4	3	2	2	2	2	2	1	4	2	2
Freon TMC	4	4	3	3	2	3	2	2	3	2	2
Freon T-P35	1	1	1	1	1	1	1	1	1	2	2
Freon TA	3	3	2	2	1	2	1	1	3	4	4
Freon TC	4	3	2	2	1	1	1	1	4	2	2
Freon MF	4	4	4	4	1	3	2	3	4	2	2
Freon BF	4	4	4	4	2	3	2	-	4	2	2
Fuel Oil	4	4	4	4	1	2	2	2	4	1	1
Fumaric Acid	3	3	2	2	1	2	2	-	2	1	1
Furan, Furfuran	4	4	4	3	4	4	4	-	-	4	4
Furfural	4	4	2	2	4	3	3	3	1	4	4
Fyrquel (Cellulube)	4	4	1	1	4	4	4	4	1	1	1
Gallic Acid	1	2	2	2	2	2	2	4	-	1	1
Gasoline	4	4	4	4	2	3	3	2	4	1	1
Gelatin	1	1	1	1	1	1	1	4	1	1	1
Glauber's Salt (aq)	2	4	2	2	4	2	2	-	-	1	1
Glucose	1	1	1	1	1	1	1	4	1	1	1
Glue	2	2	2	1	1	1	1	1	1	1	1
Glycerin	1	1	1	1	1	1	1	1	1	1	1
Glycols	1	1	1	1	1	1	1	4	1	1	1
Green Sulfate Liquor	2	2	1	1	2	2	2	1	1	1	1
Halowax Oil	4	4	4	4	4	4	4	-	4	1	1
N-Hexaldehyde	4	4	2	1	4	1	3	2	2	4	4
Hexane	4	4	4	4	1	2	2	2	4	1	1
N-Hexene-1	4	4	4	4	2	2	2	2	4	1	1
Hexyl Alcohol	2	2	3	3	1	2	2	4	2	1	1
Hydrazine	1	1	1	1	2	2	2	4	3	4	4
Hydraulic Oil (Petroleum)	4	4	4	4	1	2	2	1	3	1	1
Hydrobromic Acid	1	4	1	1	4	4	1	4	4	1	1
Hydrobromic Acid 40%	1	4	1	1	4	2	1	4	4	1	1
Hydrochloric Acid (Cold) 37%	2	4	1	1	3	2	1	4	3	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Hydrochloric Acid (Hot) 37%	4	4	3	3	4	4	2	4	4	2	1
Hydrocyanic Acid	2	2	1	1	2	2	1	-	3	1	1
Hydrofluoric Acid (Conc.) Cold	4	4	3	3	4	4	1	3	4	1	1
Hydrofluoric Acid (Conc.) Hot	4	4	4	4	4	4	3	4	4	4	4
Hydrofluoric Acid-Anhydrous	4	4	3	3	4	4	1	4	4	4	4
Hydrofluosilicic Acid (Fluosilicic Acid)	2	3	2	2	1	2	1	-	4	1	1
Hydrogen Gas	2	1	1	1	1	1	1	1	3	1	1
Hydrogen Peroxide (90%)	4	4	3	2	4	4	1	-	2	2	1
Hydrogen Sulfide (Wet) Cold	4	4	1	1	4	2	2	-	3	4	3
Hydrogen Sulfide (Wet) Hot	4	4	1	1	4	3	3	-	3	4	3
Hydroquinone	2	4	2	2	3	4	4	-	-	2	1
Hypochlorous Acid	2	4	2	2	4	4	4	-	-	1	1
Iodine Pentafluoride	4	4	4	4	4	4	4	4	4	4	4
Iodoform	4	4	4	4	-	4	-	-	-	3	2
Isobutyl Alcohol	1	2	1	1	2	1	1	4	1	1	1
Isocetane	4	4	4	4	1	2	2	2	4	1	1
Isophorone	4	4	3	3	4	4	4	3	4	4	4
Isopropyl Acetate	4	4	2	2	4	4	4	4	4	4	4
Isopropyl Alcohol	1	2	1	1	2	2	1	3	1	1	1
Isopropyl Chloride	4	4	4	4	4	4	4	4	4	1	1
Isopropyl Ether	4	4	4	4	2	3	3	2	4	4	4
Kerosene	1	1	1	1	1	2	1	1	1	1	1
Lacquers	4	4	4	4	4	4	4	4	4	4	2
Lacquer Solvents	4	4	4	4	4	4	4	4	4	4	4
Lactic Acid (Cold)	1	1	1	1	1	1	1	-	1	1	1
Lactic Acid (Hot)	4	4	4	4	4	4	3	-	2	1	1
Lard	4	4	2	2	1	2	1	1	2	1	1
Lavender Oil	4	4	4	4	2	4	4	4	4	1	1
Lead Acetate (aq)	1	4	1	1	2	2	4	4	4	4	4
Lead Nitrate (aq)	1	1	1	1	1	1	1	-	2	1	1
Lead Sulfamate (aq)	2	2	1	1	2	1	1	-	2	1	1
Ligroin (Benzine) (Nitrobenzine) (Pet Ether)	4	4	4	4	1	2	3	2	4	1	1
Lime Bleach	1	2	1	1	1	2	2	-	2	1	1
Lime Sulfur	4	4	1	1	4	1	1	-	1	1	1
Lindol (Hydraulic Fluid)	4	4	1	1	4	4	4	4	3	2	1
Linoleic Acid	4	4	4	4	2	4	4	-	2	2	1
Linseed Oil	4	4	3	3	1	2	2	2	1	1	1
Liquefied Petroleum Gas	4	4	4	4	1	2	2	1	3	1	1
Lubricating Oils (Petroleum)	4	4	4	4	1	2	2	2	4	4	1
Lye	2	2	1	1	2	2	1	4	2	2	1
Magnesium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Magnesium Hydroxide (aq)	2	2	1	1	2	1	1	4	-	1	1
Magnesium Sulfate (aq)	2	2	1	1	1	1	1	-	1	1	1
Maleic Acid	3	3	2	2	4	3	4	-	-	1	1
Maleic Anhydride	3	3	2	2	4	3	4	-	-	4	3
Malic Acid	3	3	2	2	1	3	2	-	2	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Mercury Chloride (aq)	1	1	1	1	1	1	1	-	-	1	1
Mercury	1	1	1	1	1	1	1	1	-	1	1
Mesityl Oxide	4	4	2	2	4	4	4	4	4	4	4
Methane	4	4	4	4	1	2	2	3	4	1	1
Methyl Acetate	3	3	1	1	4	2	4	4	4	4	4
Methyl Acrylate	4	4	2	2	4	2	4	4	4	4	4
Methylacrylic Acid	4	4	2	2	4	2	4	4	4	4	4
Methyl Alcohol	1	1	1	1	1	1	1	4	1	4	1
Methyl Bromide	4	4	4	4	2	4	4	-	-	1	1
Methyl Butyl Ketone (Propyl Acetone)	4	4	1	1	4	4	4	4	3	4	4
Methyl Cellosolve	4	4	2	2	3	3	2	4	4	4	4
Methyl Chloride	4	4	3	3	4	4	4	4	4	2	1
Methyl Cyclopentane	4	4	4	4	4	4	4	4	4	1	1
Methylene Chloride	4	4	4	3	4	4	4	4	4	2	2
Methyl Ether (Dimethyl Ether)	4	4	4	4	1	3	3	-	1	4	4
Methyl Ethyl Ketone	4	4	2	1	4	3	4	4	4	4	4
Methyl Formate	4	4	2	2	4	2	2	-	-	4	4
Methyl Isobutyl Ketone	4	4	3	2	4	4	4	4	4	4	4
Methyl Methacrylate	4	4	4	3	4	4	4	-	4	4	4
Methyl Oleate	4	4	2	2	4	4	4	-	-	2	1
Methyl Salicylate	3	3	2	2	4	4	4	-	-	2	1
Milk	1	1	1	1	1	1	1	4	1	1	1
Mineral Oil	4	4	3	3	1	2	2	1	-	1	1
Monochlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Monomethyl Aniline	4	4	2	2	4	4	4	4	-	2	2
Monoethanol Amine	2	2	2	1	4	4	4	4	2	4	4
Monomethyl Ether (Methyl Ether) (Dimethyl Ether)	4	4	4	4	1	3	2	-	1	4	4
Monovinyl Acetylene	2	2	2	2	1	2	2	-	2	1	1
Mustard Gas	1	2	1	1	-	1	1	-	1	1	1
Naphtha	4	4	4	4	2	3	4	2	4	1	1
Naphthalene	4	4	4	4	4	4	4	2	4	1	1
Naphthalenic Acid	4	4	4	4	2	4	4	-	4	1	1
Natural Gas	2	2	4	4	1	1	1	2	1	1	1
Neats Foot Oil	4	4	2	2	1	4	4	-	2	1	1
Neville Acid	4	4	2	2	4	4	4	-	4	1	1
Nickel Acetate (aq)	1	4	1	1	2	2	4	4	4	4	4
Nickel Chloride (aq)	1	1	1	1	1	1	1	3	1	-	1
Nickel Sulfate (aq)	2	2	1	1	1	1	1	3	1	1	1
Niter Cake	1	1	1	1	1	1	1	1	1	1	1
Nitric Acid (Conc.)	4	4	4	4	4	4	2	4	4	2	1
Nitric Acid (Dilute)	4	4	2	2	4	2	1	3	2	1	1
Nitric Acid-Red Fuming	4	4	4	4	4	4	4	4	4	3	2
Nitrobenzene	4	4	1	1	4	4	4	4	4	2	1
Nitrobenzene (Petroleum Ether)	4	4	4	4	1	2	3	2	4	1	1
Nitroethane	2	2	2	2	4	3	2	4	4	4	4
Nitrogen	1	1	1	1	1	1	1	1	1	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Nitrogen Tetroxide	4	4	3	3	4	4	4	4	4	4	4
Nitromethane	2	2	2	2	4	2	3	4	4	4	4
Octachlorotoluene	4	4	4	4	4	4	4	3	4	1	1
Octadecane	4	4	4	4	1	2	2	1	4	1	1
N-Octane	4	4	4	4	2	2	2	4	4	1	1
Octyl Alcohol	2	2	3	3	2	1	2	4	2	1	1
Oleic Acid	4	4	4	4	3	3	3	2	4	2	2
Oleum Spirits	4	4	4	4	2	3	2	3	4	1	1
Olive Oil	4	4	2	2	1	2	2	1	3	1	1
O-Dichlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Oxalic Acid	2	2	1	1	2	2	2	-	2	1	1
Oxygen-Cold	2	2	1	1	2	1	1	1	1	1	1
Oxygen-(200-400°F)	4	4	4	3	4	4	4	4	2	2	1
Ozone	4	4	2	1	4	3	1	1	1	1	1
Paint Thinner, Duco	4	4	4	4	4	4	4	4	4	2	1
Palmitic Acid	2	2	2	2	1	2	3	1	4	1	1
Peanut Oil	4	4	3	3	1	3	2	2	1	1	1
Perchloric Acid	4	4	2	2	4	2	2	4	4	1	1
Perchloroethylene	4	4	4	4	2	4	4	4	4	1	1
Petroleum-Below 250°F	4	4	4	4	1	2	2	2	2	1	1
Petroleum-Above 250°F	4	4	4	4	4	2	4	4	4	2	1
Phenol (Carbolic Acid)	4	-	2	2	4	3	2	3	4	1	1
Phenylbenzene (Biphenyl) (Diphenyl)	4	4	4	4	4	4	4	4	4	1	1
Phenyl Ethyl Ether	4	4	4	4	4	4	4	4	4	4	4
Phenyl Hydrazine	1	2	2	2	4	4	4	-	-	2	1
Phorone (Diisopropylidene Acetone)	4	4	3	3	4	4	4	4	4	4	4
Phosphoric Acid-20%	2	2	2	1	2	2	1	1	2	1	1
Phosphoric Acid-45%	3	3	2	1	4	2	2	1	3	1	1
Phosphorus Trichloride	4	4	1	1	4	4	4	-	-	1	1
Pickling Solution	4	4	3	3	4	4	2	4	4	2	1
Picric Acid	2	2	2	2	2	1	2	2	4	1	1
Pinene	4	4	4	4	2	3	3	2	4	1	1
Pine Oil	4	4	4	4	4	4	4	-	4	1	1
Piperidine	4	4	4	4	4	4	4	4	4	4	4
Plating Solution-Chrome	4	4	1	1	-	4	4	-	4	1	1
Plating Solution-Others	4	4	1	1	1	4	1	-	4	1	1
Polyvinyl Acetate Emulsion	2	4	1	1	-	2	2	-	-	-	1
Potassium Acetate (aq)	1	4	1	1	2	2	1	4	4	4	4
Potassium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Cupro Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Dichromate (aq)	2	2	1	1	1	1	1	2	1	1	1
Potassium Hydroxide (aq)	2	2	1	1	2	2	1	4	3	4	4
Potassium Nitrate (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Sulfate (aq)	2	1	1	1	1	1	2	1	1	1	1
Producer Gas	4	4	4	4	1	2	2	1	2	1	1
Propane	4	4	4	4	1	2	2	3	4	1	1
i-Propyl Acetate	4	4	2	2	4	4	4	4	4	4	4

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
n-Propyl Acetate	4	4	2	2	4	4	4	4	4	1	1
Propyl Acetone (Methyl Butyl Ketone)	4	4	1	1	4	4	4	4	3	4	4
Propyl Alcohol	1	1	1	1	1	1	1	4	1	1	1
Propyl Nitrate	4	4	2	2	4	4	4	-	4	4	4
Propylene	4	4	4	4	4	4	4	4	4	1	1
Propylene Oxide	4	4	2	2	4	4	4	4	4	4	4
Pydraul, 10E, 29 ELT	4	4	1	1	4	4	4	4	4	1	1
Pydraul, 30E, 50E, 65E, 90E	4	4	1	1	4	4	4	4	1	1	1
Pydraul, 115E	4	4	1	1	4	4	4	4	4	1	1
Pydraul, 230E, 312C, 540C	4	4	4	4	4	4	4	4	4	1	1
Pyranol, Transformer Oil	4	4	4	4	1	2	3	2	4	1	1
Pyridine	4	4	2	2	4	4	4	-	4	4	4
Pyroigneous Acid	4	4	2	2	4	2	2	4	-	4	4
Pyrrrole	3	3	4	3	4	4	4	4	2	4	4
Radiation	3	3	4	2	3	2	3	3	3	3	3
Rapeseed Oil	4	4	1	1	2	2	2	2	4	1	1
Red Oil (MIL-H-5606)	4	4	4	4	1	2	2	1	4	1	1
RJ-1 (MIL-F-25558 B)	4	4	4	4	1	2	2	1	4	1	1
RP-1 (MIL-F-25576 C)	4	4	4	4	1	2	2	1	4	1	1
Sal Ammoniac	1	1	1	1	1	1	1	1	2	1	1
Salicylic Acid	1	2	1	1	2	1	-	-	-	1	1
Salt Water	1	1	1	1	1	2	1	2	1	1	1
Sewage	2	2	2	2	1	2	1	4	2	1	1
Silicate Esters	4	4	4	4	2	1	1	1	4	1	1
Silicone Greases	1	1	1	1	1	1	1	1	3	1	1
Silicone Oils	1	1	1	1	1	1	1	1	3	1	1
Silver Nitrate	1	1	1	1	2	1	1	1	1	1	1
Skydrol 500	4	4	2	1	4	4	4	4	3	4	4
Skydrol 7000	4	4	1	1	4	4	4	4	3	2	1
Soap Solutions	2	1	1	1	1	2	1	3	1	1	1
Soda Ash	1	1	1	1	1	1	1	-	1	1	1
Sodium Acetate (aq)	1	4	1	1	2	2	1	4	4	4	4
Sodium Bicarbonate (aq) (Baking Soda)	1	1	1	1	1	1	1	-	1	1	1
Sodium Bisulfite (aq)	1	2	1	1	1	1	1	-	1	1	1
Sodium Borate (aq)	1	1	1	1	1	1	1	-	1	1	1
Sodium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Sodium Cyanide (aq)	1	1	1	1	1	1	1	-	1	1	1
Sodium Hydroxide (aq)	1	1	1	1	2	1	1	4	2	2	1
Sodium Hypochlorite (aq) (Chlorox)	4	4	2	2	2	1	1	4	2	1	1
Sodium Metaphosphate (aq)	1	1	1	1	1	2	2	-	-	1	1
Sodium Nitrate (aq)	2	1	1	1	2	2	1	-	4	1	1
Sodium Perborate (aq)	2	2	1	1	2	2	2	-	2	1	1
Sodium Peroxide (aq)	2	2	1	1	2	2	2	4	4	2	1
Sodium Phosphate (aq)	1	1	1	1	1	2	1	1	4	1	1
Sodium Silicate (aq)	1	1	1	1	1	1	1	-	-	1	1
Sodium Sulfate (aq)	2	2	1	1	1	1	1	1	1	1	1
Sodium Thiosulfate (aq)	2	2	1	1	2	1	1	1	1	1	1
Soybean Oil	4	4	3	3	1	2	3	2	1	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Stannic Chloride (aq)	1	1	1	1	1	2	1	-	2	1	1
Stannous Chloride (aq)	1	1	1	1	1	1	1	-	2	1	1
Steam Under 300°F	4	4	2	1	4	3	4	4	3	4	2
Steam Over 300°F	4	4	4	3	4	4	4	4	4	4	4
Stearic Acid	2	2	2	2	2	2	2	1	2	1	1
Stoddard Solvent	4	4	4	4	1	2	4	1	4	1	1
Styrene	4	4	4	4	4	4	4	3	4	1	1
Sucrose Solution	1	1	1	1	1	2	2	4	1	2	1
Sulfite Liquors	2	2	2	2	2	2	2	-	4	1	1
Sulfur	4	4	1	1	4	1	1	-	3	1	1
Sulfur Chloride (aq)	4	4	4	4	3	3	2	-	3	1	1
Sulfur Dioxide (Dry)	2	2	2	1	4	4	2	-	2	2	1
Sulfur Dioxide (Wet)	4	4	1	1	4	2	1	-	2	2	1
Sulfur Dioxide (Liquified Under Pressure)	4	4	2	1	4	4	4	-	2	2	1
Sulfur Hexafluoride	4	4	1	1	2	1	2	-	2	1	1
Sulfur Trioxide	2	2	2	2	4	4	4	-	2	1	1
Sulfuric Acid (Dilute)	3	3	2	2	3	2	1	3	4	1	1
Sulfuric Acid (Conc.)	4	4	4	3	4	4	1	4	4	1	1
Sulfuric Acid (20% Oleum)	4	4	4	4	4	4	4	4	4	1	1
Sulfurous Acid	2	2	2	2	2	2	1	3	4	3	2
Tannic Acid	1	2	1	1	1	1	1	1	2	1	1
Tar, Bituminous	4	4	3	3	2	3	4	-	2	1	1
Tartaric Acid	3	4	2	2	1	2	1	1	1	1	1
Terpineol	4	4	3	3	2	4	4	2	-	1	1
Tertiary Butyl Alcohol	2	2	2	2	2	2	2	4	2	1	1
Tertiary Butyl Catechol	4	2	2	2	4	2	2	4	-	1	1
Tertiary Butyl Mercaptan	4	4	4	4	4	4	4	4	4	1	1
Tetrabromoethane	4	4	4	4	4	4	4	-	4	1	1
Tetrabromomethane	4	4	4	4	4	4	-	-	4	1	1
Tetrabutyl Titanate	2	2	2	1	2	2	1	-	-	1	1
Tetrachloroethylene	4	4	4	4	4	4	4	4	4	1	1
Tetraethyl Lead	4	4	4	4	2	2	4	-	-	1	1
Tetrahydrofuran	4	4	3	3	4	4	4	3	4	4	4
Tetralin	4	4	4	4	4	4	4	-	4	2	1
Thionyl Chloride	4	4	4	3	4	4	4	4	-	2	1
Titanium Tetrachloride	4	4	4	4	2	4	4	4	4	1	1
Toluene	4	4	4	4	4	4	4	4	4	2	1
Toluene Diisocyanate	4	4	2	2	4	4	4	-	4	4	3
Transformer Oil	4	4	4	4	1	2	3	1	2	1	1
Transmission Fluid Type A	4	4	4	4	1	2	2	1	2	1	1
Triacetin	2	2	1	1	2	2	2	4	-	4	3
Triaryl Phosphate	4	4	1	1	4	4	4	4	3	1	1
Tributoxy Ethyl Phosphate	2	2	1	1	4	4	4	4	-	1	1
Tributyl Mercaptan	4	4	4	4	4	4	4	-	4	1	1
Tributyl Phosphate	2	4	2	2	4	4	4	4	4	4	4
Trichloroacetic Acid	3	2	2	2	2	4	4	4	-	4	3
Trichloroethane	4	4	4	4	4	4	4	4	4	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
2 = Moderate Effect
 4 = Not Recommended
 = Insufficient Data

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
Trichloroethylene	4	4	4	4	4	4	4	4	4	1	1
Tricresyl Phosphate	4	1	1	4	4	3	4	4	3	1	1
Triethanol Amine	2	2	2	1	2	1	2	4	-	4	4
Triethyl Aluminum	4	4	3	3	4	4	4	4	-	2	1
Triethyl Borane	4	4	3	3	4	4	4	4	-	1	1
Trinitrotoluene	4	4	4	4	4	2	2	-	-	2	1
Trioctyl Phosphate	4	4	1	1	4	4	4	4	3	2	1
Tung Oil (China Wood Oil)	4	4	3	3	1	2	3	3	4	1	1
Turbine Oil	4	4	4	4	2	4	4	1	4	1	1
Turpentine	4	4	4	4	1	4	4	4	4	1	1
Unsammatical Dimethyl Hydrazine (UDMH)	1	1	1	1	2	2	1	-	4	4	4
Varnish	4	4	4	4	2	4	4	3	4	1	1
Vegetable Oils	4	4	3	3	1	3	2	-	2	1	1
Versilube F-50	1	1	1	1	1	1	1	1	3	1	1
Vinegar	2	2	1	2	2	2	1	4	1	1	1
Vinyl Chloride	4	4	4	4	4	4	4	4	-	1	1
Wagner 21B Brake Fluid	2	1	2	1	3	2	2	-	3	4	3
Water	1	1	1	1	1	1	1	3	1	1	1
Whiskey, Wines	1	1	1	1	1	1	1	2	1	1	1
White Pine Oil	4	4	4	4	2	4	4	-	4	1	1
White Oil	4	4	4	4	1	2	4	1	4	1	1
Wood Oil	4	4	4	4	1	2	3	3	4	1	1
Xylene	4	4	4	4	4	4	4	4	4	1	1
Xylylene (DI-methyl Aniline)	3	3	3	2	3	3	4	4	4	4	3
Zeolites	1	1	1	1	1	1	1	-	-	1	1
Zinc Acetate (aq)	1	4	1	1	2	2	1	4	4	4	4
Zinc Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Zinc Sulfate (aq)	2	2	1	1	1	1	1	-	1	1	1
TT-T-656b	4	4	1	1	4	4	4	4	4	4	-
VV-B-680	3	1	2	1	2	2	2	3	4	1	1
VV-G-632	4	4	4	4	1	1	1	1	3	1	1
VV-G-671c	4	4	4	4	1	1	1	1	3	1	1
VV-H-910	2	1	2	1	2	2	2	3	4	1	1
VV-I-530a	4	4	4	4	1	2	2	2	3	1	1
VV-K-211d	4	4	4	4	1	3	3	3	4	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
VV-K-220a	4	4	4	4	1	2	3	2	4	1	1
VV-L-751b	4	4	4	4	2	2	3	3	4	1	1
VV-L-800	4	4	4	4	1	2	2	2	3	1	1
VV-L-820b	4	4	4	4	1	2	2	2	3	1	1
VV-L-825a Type I	4	4	4	4	1	1	1	1	3	1	1
VV-L-825a Type II	4	4	4	4	1	1	1	1	3	1	1
VV-L-825a Type III	4	4	4	4	2	2	3	3	4	1	1
VV-O-526	4	4	4	4	1	1	1	1	3	1	1
VV-P-216a	4	4	4	4	1	2	2	2	3	1	1
VV-P-236	4	4	4	4	2	2	3	3	4	1	1
51-F-23	4	4	4	4	1	2	2	2	3	1	1
ASTM Method D-471											
1	4	4	4	4	1	1	1	1	3	1	1
2	4	4	4	4	1	2	2	2	3	1	1
3	4	4	4	4	1	2	2	2	3	1	1
MIL-L-644 B	3	3	3	3	1	3	3	3	3	-	-
MIL-L-2104 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-2105 B	4	4	4	4	1	1	1	1	3	1	1
MIL-G-2108	4	4	4	4	1	1	1	1	3	1	1
MIL-S-3136 B Type I	4	4	4	4	1	2	3	2	4	1	1
MIL-S-3136 B Type II	4	4	4	4	1	3	3	3	4	1	1
MIL-S-3136 B Type III	4	4	4	4	1	3	3	3	4	1	1
MIL-S-3136 B Type IV	4	4	4	4	1	1	1	1	3	1	1
MIL-S-3136 B Type V	4	4	4	4	1	2	2	2	3	1	1
MIL-S-3136 B Type VI	4	4	4	4	1	2	2	2	3	1	1
MIL-S-3136 B Type VII	4	4	4	4	1	3	3	3	4	1	1
MIL-L-3150 A	4	4	4	4	1	1	1	1	3	1	1
MIL-L-3503	4	4	4	4	1	2	2	2	3	1	1
MIL-L-3545-B	4	4	4	4	2	2	3	3	4	1	1
MIL-C-4339 C	4	4	4	4	1	1	1	1	3	1	1
MIL-G-4343 B	4	4	3	3	2	2	2	1	4	1	1
MIL-L-5020 A	4	4	4	4	1	1	3	2	4	1	1
MIL-J-5161 F	4	4	4	4	1	3	3	3	4	1	1
MIL-C-5545 A	4	4	4	4	2	2	3	3	4	1	1
MIL-H-5559 A	2	1	1	1	1	2	2	3	2	2	1
MIL-F-5566	1	1	1	1	1	2	2	2	1	1	1
MIL-F-5602	4	4	4	4	1	2	2	2	3	1	1
MIL-H-5606 B (Red Oil)	4	4	4	4	1	2	2	1	4	1	1
MIL-J-5624 G JP-3, JP-4, JP-5	4	4	4	4	1	3	3	3	4	1	1
MIL-O-6081 C	4	4	4	4	1	2	2	2	3	1	1
MIL-L-6082 C	4	4	4	4	1	1	1	1	3	1	1
MIL-H-6083 C	4	4	4	4	1	2	2	2	3	1	1
MIL-L-6085 A	4	4	3	4	2	3	3	3	3	1	1
MIL-L-6086 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-6387 A	4	4	3	4	1	3	3	3	3	1	1
MIL-C-6529 C	4	4	4	4	2	2	3	2	4	1	1
MIL-F-7024 A	4	4	4	4	1	2	2	2	4	1	1
MIL-H-7083 A	2	1	1	1	1	2	2	3	2	2	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheetting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
 4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
MIL-G-7118 A	4	4	3	4	1	3	3	3	3	1	1
MIL-G-7187	4	4	4	4	1	1	1	1	3	1	1
MIL-G-7421 A	4	4	3	4	1	3	3	2	3	1	1
MIL-H-7644	2	1	2	1	2	2	2	3	4	1	1
MIL-L-7645	4	4	4	4	2	2	3	3	4	1	1
MIL-G-7711 A	4	4	4	4	1	1	1	1	3	1	1
MIL-L-7808 F	4	4	3	4	1	3	3	3	3	1	1
MIL-L-7870 A	4	4	4	4	1	2	2	2	3	1	1
MIL-C-8188 C	4	4	3	4	1	3	3	3	3	1	1
MIL-A-8243 B	2	1	1	1	1	2	2	3	2	-	1
MIL-L-8383 B	4	4	4	4	1	1	1	1	3	1	1
MIL-H-8446 B (MLO-8515)	4	4	4	4	2	2	-	4	4	1	1
MIL-1-8660 B	1	1	1	1	1	1	1	1	4	1	1
MIL-L-9000 F	4	4	4	4	1	2	3	3	4	1	1
MIL-T-9188 B	4	4	1	1	4	4	4	4	4	-	-
MIL-L-9236 B	3	3	3	3	1	3	3	2	4	1	1
MIL-L-10295 A	4	4	4	4	1	2	2	2	4	1	1
MIL-L-10324 A	4	4	4	4	1	2	2	2	3	1	1
MIL-G-10924 B	4	4	4	4	1	2	2	2	3	1	1
MIL-L-11734 B	4	4	3	4	1	3	3	3	3	1	1
MIL-O-11773	4	4	3	4	1	3	3	3	3	1	1
MIL-P-12098	2	1	2	1	2	2	2	3	4	1	1
MIL-H-13862	4	4	4	4	1	2	2	2	3	1	1
MIL-H-13866 A	4	4	4	4	1	2	2	2	3	1	1
MIL-H-13910 B	2	1	2	1	2	2	2	3	4	1	1
MIL-H-13919 A	4	4	4	4	4	2	2	2	3	1	1
MIL-L-14107 B	4	4	4	4	3	1	-	-	4	1	1
MIL-L-15017	4	4	4	4	1	1	1	1	3	1	1
MIL-L-15018 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-15019 C	4	4	4	4	1	1	1	1	3	1	1
MIL-L-15719 A	3	2	2	2	2	2	2	4	4	1	1
MIL-G-15793	4	4	3	4	1	3	3	3	3	1	1
MIL-F-16929 A	4	4	3	4	1	3	3	3	3	1	1
MIL-F-16958 A	4	4	4	4	1	2	2	2	3	1	1
MIL-F-17111	4	4	4	4	1	2	2	2	3	1	1
MIL-L-17331 D	4	4	4	4	1	1	1	1	3	1	1
MIL-L-17353 A	4	4	4	4	1	3	3	2	3	1	1
MIL-L-17672 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-18486 A	4	4	4	4	1	1	1	1	3	1	1
MIL-G-18709 A	4	4	4	4	1	1	1	1	3	1	1
MIL-H-19457 B	4	4	1	1	4	4	4	4	4	-	1
MIL-F-19605	4	4	4	4	1	3	3	3	4	1	1
MIL-L-19701	4	4	3	4	1	3	3	3	3	1	1
MIL-L-21260	4	4	4	4	1	1	1	1	3	1	1
MIL-L-21568 A	2	1	1	1	1	1	-	-	4	1	1
MIL-H-22072	2	1	1	1	1	2	2	3	2	2	1
MIL-L-22396	4	4	4	4	1	1	1	1	3	1	1
MIL-L-23699 A	4	4	3	4	1	3	3	3	3	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.



Chemical Resistance Chart - Rubber Sheeting

1 = Minor Effect
 3 = Static Only
 - = Insufficient Data
2 = Moderate Effect
4 = Not Recommended

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
MIL-G-23827 A	4	4	3	4	1	3	3	3	3	1	1
MIL-G-25013 D	2	1	1	1	1	2	2	3	4	1	1
MIL-F-25172	4	4	4	4	1	3	3	3	4	1	1
MIL-L-25336 B	4	4	3	4	1	3	3	3	3	1	1
MIL-F-25524 A	4	4	4	4	1	3	3	3	4	1	1
MIL-G-25537 A	4	4	4	4	1	2	2	2	3	1	1
MIL-F-25558 B (RJ-1)	4	4	4	4	1	2	2	1	3	1	1
MIL-F-25576 C (RP-1)	4	4	4	4	1	3	3	1	4	1	1
MIL-H-25598	4	4	4	4	1	2	2	2	3	1	1
MIL-F-25656 B	4	4	4	4	1	3	3	3	4	1	1
MIL-L-25681 C	2	1	1	1	1	2	2	3	4	1	1
MIL-G-25760 A	3	3	4	4	1	3	3	2	4	1	1
MIL-L-25968	4	4	4	4	1	3	3	3	3	1	1
MIL-L-26087 A	4	4	4	4	1	1	1	1	3	1	1
MIL-G-27343	1	1	1	1	1	1	1	1	4	1	1
MIL-H-27601 A	4	4	4	4	2	2	2	3	4	1	1
MIL-G-27617	-	2	1	1	4				4	1	1
MIL-I-27686 D	2	1	1	1	1	2	2	3	2	2	1
MIL-L-27694 A	1	1	1	1	1	1	1	1	4	1	1
MIL-L-46000 A	4	4	3	4	1	3	3	3	3	1	1
MIL-H-46001 A	4	4	4	4	1	1	1	1	3	1	1
MIL-L-46002	4	4	4	4	1	1	1	1	3	1	1
MIL-H-46004	4	4	4	4	1	2	2	2	3	1	1
MIL-P-46046 A	2	1	2	1	2	2	2	3	4	1	1
MIL-H-81019 B	4	4	4	4	1	2	2	2	3	1	1
MIL-S-81087	1	1	1	1	1	1	1	1	4	1	1
O-A-548 b	2	1	1	1	1	2	2	3	2	2	2
O-T-634 b	4	4	4	4	3	4	4	4	4	1	1
P-S-661 b	4	4	4	4	1	3	3	3	4	1	1
P-D-680	4	4	4	4	1	3	3	3	4	1	1
TT-N-95 a	4	4	4	4	1	3	3	3	4	1	1
TT-N-97 B	4	4	4	4	1	3	3	3	4	1	1
TT-I-735 b	1	1	1	1	1	2	2	2	1	1	1
TT-S-735 Type I	4	4	4	4	1	2	3	2	4	1	1
TT-S-735 Type II	4	4	4	4	1	3	3	3	4	1	1
TT-S-735 Type III	4	4	4	4	1	3	3	3	4	1	1
TT-S-735 Type IV	4	4	4	4	1	1	1	1	3	1	1
TT-S-735 Type V	4	4	4	4	1	2	2	2	3	1	1
TT-S-735 Type VI	4	4	4	4	1	2	2	2	3	1	1
TT-S-735 Type VII	4	4	4	4	1	4	4	3	4	1	1

The information contained in this chemical resistance chart is to the best of our knowledge correct and should be used as a guideline only. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product specifications and properties without notification.